



# SHANDONG SANYI GROUP CO., LTD

NO.135 HUILONGSHAN RD, LONGSHAN HIGH-TECH INDUSTRIAL PARK,LINQU,  
WEIFANG,SHANDONG,CHINA

Tel: 0086- 532-68856252

Fax: 0086-536-3353966

## CHLORINATED POLYETHYLENE CPE 135A

### Applications:

Conventional chlorinated polyethylene grade for PVC

### Features:

CPE135A is a regular structure of the saturated thermoplastic resin, has good extrusion fluidity mixed with PVC.

### Product Specifications:

Analysis Items	Specification
Appearance	White Powder
Chlorine content (%)	35±2
whiteness	≥85
Hot melt(J/g)	≤2.0
Volatile matter (%)	≤0.4
Sieve residue(0.9mm aperture)	≤2.0
mpurity Particle (No/100g)	≤30
Number of spots ( 150*150 )	≤ 80
Tensile strength(Mpa)	≥8.0
Elongation at break (%)	≥650
Shore A hardness(A)	≤65
The thermal stability Time(165°C)(min)	≥8