



CALCIUM STEARATE MFLOW-30

CALCIUM STEARATE UNIFLOW is a synthetic Calcium Stearate manufactured by a novel proprietory process developed by our R & D department having tremendous experience in precipitation and particle size/morphology control technology, and recognized by the Department of Scientific and Industrial Research, Government of India. The output is a unique combination of fineness and thermal stability in the product and better dispersion in the base polymer. The product is technically far better than the currently available products, besides the assurance of consistent quality from an ISO 9001:2000 certified unit.

TYPICAL PHYSIOCHEMICAL PROPERTIES

PROPERTY	UNIT	MEFLOW-30
Colour & Appearance	-	White Free Flowing Powder
Bulk Density1,3 – Loose	gm/cc	0.28
- Compact*		0.35
Moisture (105°C)2	%	<1.0
Electrolytes	%	<1.0
Residue on 300 mesh⁵	%	<0.2
Melting Point	°C	160±5
Melt Quality	-	White with good flow, no bubbles
CaO	%	6 - 7
Fe Content	Ppm max	80
Heavy Metals as Pb	Ppm max	20
Free fatty matter	%	<1.5
pH⁴	-	8.0 - 10.5

1) At the time of packing 2) By IR Moisture Balance 3) IS: 7589-1974 (A-8) 4) IS: 12076-1986(A-2) 5) IS: 2850-1983 (A-5.1)

APPLICATION:

- As an acid scavenger in polymers processing
- As an internal lubricant in PVC and other polymers processing
- · As a water repellant in paints and other coatings

Doc. No.: UNIFLOW-4

Issue No.: 03

Issue Date: 17.11.2015

Replaces: 05.04.2010

This information and our technical advice-whether verbal, in writing or by way of trials are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sales and Delivery.

Correspondence Address:

III/230, Harsh Nagar KANPUR - 208 012. (INDIA)

Ph. :0512-2555292

Website: www.mlagroup.com Email: info@mlagroup.com















